



PRINTLAC® High-gloss 10 L 9560

Range of application

This product is an oil-based varnish with a very high degree of gloss that stands out thanks to its very quick setting and short oxidative drying characteristics. As a result, the length of time before the print sheets can be further processed (converted) is shortened.

Thanks to its rheological properties, PRINTLAC® 10 L 9560 is equally suitable for wet-on-wet and wet-on-dry varnishing.

Due to its quick setting characteristics, the product is of only limited suitability for perfecting.

This high-gloss varnish can be used either with or without fountain solution.

Contact yellowing cannot be completely ruled out when printing varnishes are used. This is caused by volatile, yellowish coloured decomposition products being formed during oxidative drying; these products can be deposited in the paper coating or even react chemically with constituents of the coating.

By conducting extensive development work, however, we have succeeded in greatly reducing the level of unfortunately unavoidable yellowing and in producing print results that are as good as free of yellowing considering an oil-based varnishing system has been used.

Special characteristics

- Maximum gloss.
- Fast oxidative drying.
- Medium setting.
- Good pile behaviour.
- Good rub resistance.
- Little tendency to yellowing.

Advantages of print varnishes over other coating systems

In the field of package printing, print varnishes have now largely been replaced by alternative coating systems, for example by dispersion coatings. In other areas, however, the use of print varnishes is essential.

Some of the reasons for this:

- They guarantee spot varnishing true to register.
- It is possible to coat light-weight papers with the substrate remaining dimensionally stable.
- Oil-based varnishes can be seen as unpigmented offset printing inks. They are therefore handled in the same way, which includes the use of the same washing mediums. There is no requirement for the inks to possess particular fastness properties (for example resistance to solvents or alkalis).

Special remarks

Note should be taken of the following when using print varnishes:

In contrast with dispersion coatings and UV coatings, print varnishes are comparatively slow-drying. The mechanism of oxidative drying, which produces stable coating films in print varnishes as a result of the cross-linking of fatty acid chains, can occupy several hours or even days, depending on the drying conditions. Drying can be accelerated by the use of IR radiators. However, pile temperatures of more than 35 °C must always be avoided as there is a risk of blocking. The use of inks in pre-printing that stay fresh can result in the delaying of varnish drying, especially on papers with low absorption capacity.

Contact yellowing cannot be completely ruled out when print varnishes are used. The cause of this is that volatile, yellowish coloured fission products are formed during oxidative drying; these products can be deposited in the paper coating or even react chemically with constituents of the coating.

Standard print varnishes are not suitable for finishing food packaging. The fission products necessarily formed as part of the oxidative drying process can affect the smell and taste of the contents which prohibits their use.

Printing additives

The specified print varnish is ready for printing and can normally be used without the help of additives. If in exceptional cases it is necessary to reduce the tack for papers that are particularly susceptible to picking, **Linseed Oil/Printing Oil 1405** should be used.

Labelling

German Hazardous Substances Ordinance (GefStoffV): none

Safety data sheet available on request.

How supplied

Standard container 2.5 kg

Special sizes on request.

Contact addresses for advice and further information: www.hubergroup.de

This Technical information reflects the current state of our knowledge. It is designed to inform and advise. We assume no liability for correctness. Modifications may be made in the interest of technical improvement.

All product, brand and company names used in these Technical Information sheets may be registered trademarks of their respective owners.